

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

COPIE



2

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : 530/811 C08J 7/18, G01N 33/543 // C07K 17/06, C12N 11/06		A1	(11) International Publication Number: WO 96/31557 (43) International Publication Date: 10 October 1996 (10.10.96)
(21) International Application Number: PCT/DK96/00167 (22) International Filing Date: 3 April 1996 (03.04.96) (30) Priority Data: 0425/95 7 April 1995 (07.04.95) DK (71)(72) Applicants and Inventors: JACOBSEN, Mogens, Havsteen [DK/DK]; Ålekistevej 225, 1, DK-2770 Vanløse (DK). KOCH, Troels [DK/DK]; Funkiavej 47, DK-2300 Copenhagen S (DK). (74) Agent: HOFMAN-BANG & BOUTARD, LEHMANN & REE A/S; Adelgade 15, DK-1304 Copenhagen K (DK).		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published With international search report.	
(54) Title: METHOD OF PHOTOCHEMICAL IMMOBILIZATION OF LIGANDS USING QUINONES			
(57) Abstract A method of immobilizing a ligand (L) to the surface (P) of a carbon-containing substrate material; said method comprising: a photochemical step of linking of one or more photochemically reactive compounds (Q) to a carbon-containing material surface (P); wherein the photochemically reactive compound (Q) is a quinone compound containing a cyclic hydrocarbon, or from 2 to 10 fused cyclic hydrocarbons, with at least two conjugated carbonyl groups; and wherein the photochemical step comprises irradiation of the photochemically reactive compound (Q) with non-ionizing electromagnetic radiation having a wavelength in the range from UV to visible light.			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Centre African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

Method of photochemical immobilization of ligands using quinones.

DESCRIPTION

5

1. BACKGROUND OF THE INVENTION

The present invention relates to a method of modifying a polymer surface by covalent attachment of functional compounds, also designated ligands.

10

The Technical Field

Products made of synthetic or natural polymers having modified surfaces are very important in many technical areas.

15

Surface modification of polymers by the introduction of various functional groups or the covalent attachment of biologically active molecules has been the subject of increased research in recent years in such different areas as the development of novel biocompatible implants, for biosensors and biomaterials, for affinity chromatography, for surface resistant materials, for biosensors, and for covalent immobilization of high or low molecular weight molecules in ELISA assays.

20

25

Prior Art

Thermochemical Methods

30

Most methods involve sequential treatment of the polymer surface with chemical reagents to introduce functional groups to function as handles for coupling of a functional compound also called ligand. However, these methods usually employ hazardous chemicals and several

35

time-consuming steps. In addition to this, only a limited number of methods are described in which the mechanical and optical properties of the polymer can be preserved. A method of introducing primary amino groups onto polystyrene tubes using thermochemical reactions and onto microtitre plates has been described by Alexio, J.A.G.; Swaminathan, B; Minnich, S.A.; Wallshein, V.A.; J. Immunoassay 1985, 6, 391-407.

10 Radioanalytical Methods

EP-A-O 155 252 discloses a method of preparing an immunoreactive solid phase wherein a biologically active molecule is covalently bound to functional groups of vinyl monomers radiation grafted to a solid polymer surface. Grafting requires an adequate radiation dose under an inert atmosphere using radiation such as ultraviolet or ionizing radiation. Specific examples using 0,25 Mrad/h ⁶⁰Co irradiation source for 10-12 hours are given.

International application no. WO 91/02768 discloses radio-derivatized polymers produced by contacting non-polymerizable conjugands, such as quinones or compounds from which quinones or quinoid structures are generated during radio-derivatization, with radiolyzable polymers, such as polystyrene, in the presence of high energy gamma rays. The radio-derivatized polymers are suitable for introducing anchoring groups for covalent immobilization or for fixing of molecules on polymer surfaces with or without cross-linkers or with activators such as carbodiimides.

A disadvantage of radio-derivatization is the use of ionizing high energy gamma rays which requires costly health physical precautions in carrying out the method.

Photochemical Methods

5 A number of photochemical methods of modifying polymer surfaces are also known. In these methods a desired ligand (L) - often a sensitive biomolecule - is immobilized on the polymeric material surface (P) through a photochemically reactive group (Q) and a spacer (S) and optionally a thermochemical reactive group (T).

10

In general, the covalent attachment of the desired molecule (L) to the surface can be established in three ways:

15 1) The photochemically reactive group (Q) which is coupled - via a spacer (S) - to a thermochemical reactive group (Q-S-T) is bound covalently to the surface (P) by a photochemical reaction (P-Q-S-T). Subsequently, the desired molecule (L) is coupled to the surface (P-Q-S-T)
20 by thermochemical reaction (P-Q-S-T-L).

2) The photochemically reactive group (Q) which is coupled directly - via a spacer (S) - to the desired molecule (Q-S-L) is bound to the surface (P) by a
25 photochemical reaction (P-Q-S-L).

3) The photochemically reactive group (Q) is coupled covalently to the surface (P) by a thermochemical reaction (P-Q). Subsequently, the desired molecule (L) is
30 coupled to the surface (P-Q) by a photochemical reaction (P-Q-L).

The first two strategies are potentially the most flexible ones and allow control of the orientation of the
35 immobilized ligand.

EP-A2-0 319 953 discloses a photochemical method of modifying a polymer surface by immobilizing an optionally substituted two or three membered heterocyclic compound to the surface of the polymer using electromagnetic
5 irradiation with a wavelength shorter than 700 nm. Preferred compounds are optionally substituted coumarins, benzofurans, indols, and angelicins. Particularly, optimally substituted psoralens are preferred.

10 A disadvantage of this method is that psoralens are multifunctional compounds which are not easy to synthesize. They are expensive and not chemically stable, e.g. spacers containing primary amines (as a functional group) can not be introduced onto the surface, because
15 the amine will react with the psoralen.

When irradiated with UV light having a short wavelength, a secondary amine placed in the end position and coupled - via a spacer - to psoralen can be photochemically bound
20 to a polystyrene surface. When biotin is coupled to the spacer derivative, biotin can also be photochemically bound to polystyrene surfaces and polymethyl-methacrylate particles. The method cannot be considered to be generally applicable, as only these two examples work
25 satisfactorily. The photochemical mechanism has not been fully understood, but it is known that psoralen derivatives react with double bonds in a 2+2 cyclo addition reaction when irradiated with UV light.

30 A number of patent publications US-A-4 722 906, US-A-4 973 493, US 5 002 582 and PCT/US88/04491, assigned to Biometric Systems Inc., disclose methods for photochemical modification of polymer surfaces. The patent publications essentially describe methods involving
35 activating latent reactive groups selected from the group consisting of those able to generate free radicals,

carbenes, nitrenes and excited states of ketones, and covalently bonding thereof to a solid surface.

The disclosed latent reactive groups responsive to ultra-violet, visible or infrared portions of the electromagnetic spectrum are: azides, acylazides, azido formates, sulfonyl azides, phosphoryl azides; diazo compounds such as diazoalkanes, diazoketones, diazoacetates, beta-ketone-alpha-diazoacetates; aliphatic azo compounds, diazirines, ketone, diphenylketone and photoactivable ketones such as benzophenone and acetophenone; and peroxy compounds such as dialkyl- and diacyl peroxides and peroxyesters.

Latent reactive groups, which upon irradiation with high energy UV light generates highly reactive radicals, carbenes or nitrenes, suffer from a number of drawbacks. Such species are extremely reactive and will either rearrange or immediately react with most organic compounds, organic solvents and water. When the irradiation takes place in a solution, this results in loss of photoreagent and inefficient or reaction with the polymer surface. The simple precursors requires long irradiation times (typically 12 hours) which makes the application of these as photoreactive groups time consuming, inefficient and not suitable for immobilization of sensitive biomolecules.

Nothing is indicated nor suggested about photochemical coupling using quinones as the photoreactive group.

2. DISCLOSURE OF THE INVENTION

It is an object of the present invention to provide a photochemical method of immobilizing a desired ligand on

a carbon-containing material surface which method does not suffer from the drawbacks described above.

5 A particular object of the invention is to provide a photochemical method which can be used generally to immobilize ligands on carbon-containing material surfaces.

10 Another particular object is to provide a photochemical method of immobilizing a ligand on a carbon-containing material surface which method is easier and less expensive to carry out and control, and which method is optimally faster than the known methods.

15 A further object of the present invention is to provide a photochemical method of immobilizing ligands on carbon-containing material surfaces, where the ligands are not subjected to damaging treatments and therefore substantially maintain their functions, even when the
20 ligands are sensitive biomolecules.

This object is achieved by providing a method of immobilizing a ligand (L) to the surface (P) of a carbon-containing substrate material; said method comprising:
25

a photochemical step of linking of one or more photochemically reactive compounds (Q) to a carbon-containing material surface (P);

30 said carbon-containing material surface (P) being linked to the photochemically reactive compound (Q) either directly or via one or more spacers (S₁); and

said photochemically reactive compound (Q) being linked
35 to one or more ligands (L) either directly or optionally

via one or more spacers (S) and/or thermochemically reactive compounds (T);

5 said spacers (S₁) and (S) being, equal or different, thermochemically or photochemically reactive or non-reactive spacers;

10 wherein the photochemically reactive compound (Q) is a quinone compound selected from the group consisting of monomeric quinone compounds, dimeric quinone compounds, and symmetrical or asymmetrical oligomeric quinone compounds;

15 said quinone compound (Q) containing a cyclic hydrocarbon, or from 2 to 10 fused cyclic hydrocarbons, said quinone compound having at least two conjugated carbonyl groups, the number of which does not exceeding twice the number of fused cyclic hydrocarbons;

20 said quinone compound (Q) optionally being substituted with substituents (R) which do not result in steric hindrance to the immobilization of the ligand (L) or do not disturb the photochemistry; and

25 wherein the photochemical step comprises irradiation of the photochemically reactive compound (Q) with non-ionizing electromagnetic radiation having a wavelength in the range from UV to visible light.

30 The invention is based on the surprising finding that said quinone compounds as defined in claim 1 can be used as the photochemically reactive compound with very good results.

35

Quinone compounds are known as photochemically reactive compounds, but their use as photochemically reactive coupling compounds has never been suggested, even though there has been a rush in the development of new methods for immobilization of ligands to polymer surfaces.

Quinone Compounds

Quinone compounds are defined as compounds comprising at least 2 conjugated carbonyl groups placed in at least one cyclic hydrocarbon structure. Such compounds are well-known to a person skilled in the art.

The quinones suitable for use in the method according to the present invention are quinone, quinone dimers or oligomers of quinones, the latter having symmetrical or asymmetrical bonded quinones.

The quinone compound contains a cyclic hydrocarbon, or from 2 to 10 fused cyclic hydrocarbons, having at least two conjugated carbonyl groups. The number of carbonyl groups does not exceed twice the number of fused cyclic hydrocarbons.

The cyclic hydrocarbons may be fused in any position isomer.

The quinone compound is optionally being substituted with substituents (R) which do not result in steric hindrance to the immobilization of the ligand (L) or do not disturb the photochemistry, e.g. that the substituent has a chromophore which inhibits the activation of the quinone, e.g. by fluorescence, phosphorescence, radiation less transition, etc.

The cyclic hydrocarbons may independently of each other be of any ring size but are preferentially 5, 6, 10, 14, 18 carbon atom-membered aromatic rings which independently of each other may comprise one or several
5 hetero atoms selected among -N-, -NH-, and -O-. The conjugated carbonyl groups may be located in any of these rings in any position provided that the quinoid structure is maintained.

10 Applicable Basic Quinone Compounds

Illustrations of applicable basic quinone compounds are shown in Fig. 1, wherein the compounds I-XXXVI may be substituted with one or more of the substituents R
15 defined below.

Particularly Preferred Quinones

Particularly preferred quinones are claimed in claims 3
20 and 4.

In the preferred embodiment having the general formulas (XXXVII), (XXXVIII), and (XXXIX), also shown in Fig. 2, the letters m, n and o designate 0 or integers from 1-8, the sum of m, n and o being 8 or less; 1 indicates 0 or
25 an integer from 1 to two times n; r and q indicate 0, 1 or 2; k indicates 0 or an integer from 1 to 2 times m; and t indicates 0 or an integer from 1 to 2 times o.

30 It is preferred that the sum of m, n and o is 8 or less.

R designates substituents as defined below.

The substituents are selected independently of each
35 other. Preferably the total sum of the number of sub-

stituents ($l + r + k + q + t$) is less than the number of fused cyclic hydrocarbon compounds.

Specifically preferred quinones are selected from the group consisting of:

anthraquinones (V,VI,VII,X,XI,XIII,XXVIII), phenanthrene-quinones (VIII,IX,XII), benzoquinones (I,II), naphthoquinones (III,IV,XXVII), and compound (XXVI,XXIX), particularly anthraquinones, phenanthrenequinones, and compound (XXVI).

Substituents R

The choice of substituents are important in controlling the solubility of the quinone and the overall affinity of the quinone towards the material surface; e.g. introduction of charged substituents will enhance the solubility in water and also increase or decrease the affinity towards charged material surfaces via attractive or repulsive ionic interactions. Thus, the substituents R may be selected in relation to the optimal hydrophobic/-hydrophilic character which depends on the system and the solvent in which the photoreactive step takes place. Optimally, the quinone compound is partly soluble in the solvent.

The quinones are preferably substituted with a number of substituents which are less than three times the number of fused cyclic hydrocarbons, but they may, however, be completely saturated with substituents, provided that the quinoid structure is maintained.

Specifically the substituents (R) can themselves be quinones.

The useful substituents R may independently of each other be selected among the group consisting of:

functional groups comprising $-\text{NO}_2$, $-\text{SO}_3^-$, $-\text{SO}_2^-$, $-\text{CN}$,
5 $-\text{PO}_3^{2-}$, $-\text{PO}_2^-$, $-\text{COOH}$, halogen, i.e. $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$,
primary amines, secondary amines and tertiary amines, or
derivatives thereof; and

hydrocarbyls which may be substituted with: $-\text{NO}_2$, $-\text{SO}_3^-$,
10 $-\text{CN}$, $-\text{PO}_3^{2-}$, $-\text{PO}_2^-$, $-\text{COOH}$, halogen, i.e. $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$,
epoxide, and $-\text{H}$;

said hydrocarbyls comprising alkyl having from 1-30 C-
atoms, alkenyl having from 1-30 C-atoms, alkynyl having
15 from 1-30 C-atoms, aryl having from 6-50 C-atoms,
preferably 6-18 C-atoms, and derivatives thereof
comprising combinations of these with equal or different
substituents for the functional groups defined above; and

20 said hydrocarbyl being straight/branched-chained,
symmetric/asymmetric, chiral/achiral; containing one or
more heteroatoms selected from the group consisting of
 $-\text{N}-$, $-\text{NH}-$, and $-\text{O}-$; or being fused, aromatic systems;

25 said fused, aromatic system containing one or more
heteroatoms being heterocyclyl selected from the group
consisting of pyridyl, imidazolyl, pyrimidinyl,
pyridazinyl, quinolyl, acridinyl, imidazolyl, pyrrolyl,
furyl, isoxazolyl, oxazolyl, which may be bound and/or
30 fused in any position, and derivatives thereof comprising
combinations of these with equal or different
substituents as for the functional groups defined above.

Preferred substituents R are selected from the group
35 consisting of: functional groups comprising $-\text{NO}_2$, $-\text{SO}_3^-$,
 $-\text{SO}_2^-$, $-\text{CN}$, $-\text{PO}_3^{2-}$, $-\text{PO}_2^-$, $-\text{COOH}$, halogen, i.e. $-\text{F}$, $-\text{Cl}$,

-Br, -I, primary amines, secondary amines and tertiary amines, or derivatives thereof; and hydrocarbyls which may be substituted with: $-\text{NO}_2$, $-\text{SO}_3^-$, $-\text{CN}$, $-\text{PO}_3^{2-}$, $-\text{PO}_2^-$, $-\text{COOH}$, halogen, i.e. -F, -Cl, -Br, -I, epoxide, and -H.

5

Preferred alkyls are methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decanyl, undecanyl, dodecanyl, tridecanyl, tetradecanyl, pentadecanyl, hexadecanyl, heptadecanyl, octadecanyl, nonadecanyl, eicocanyl, straight or branched, with one or more double or triple bonds.

10

Preferred aryls are phenyl, naphtyl, biphenyl, tolyl, benzyl, cumenyl, mesityl, xylyl, pentalenyl, indenyl.

15

Non-ionizing Electromagnetic Irradiation

The electromagnetic radiation is chosen in order to activate the quinones. It is a non-ionizing electromagnetic radiation having a wavelength in the range from UV to visible, preferably shorter than 700 nm.

20

Normally the electromagnetic radiation is selected with a band of wavelengths in the range from 15 to 50 nm around a center wavelength. This band of wavelengths is chosen in order to be able to activate the quinones with electromagnetic radiation providing maximal absorption of the quinone chromophores.

25

The UV-light has a wavelength from UV to visible in order to minimize the interaction of the light with functional groups and sensitive ligands or biomolecules covalently linked to the quinones, such groups typically sensitive to electromagnetic radiation having wavelengths shorter than UV, whereby they are destroyed. It is thus possible to select an electromagnetic radiation having a wave-

30

35

length in the wide range of wavelength where the quinones absorb electromagnetic radiation which selected radiation specifically activates the photochemically active group of interest.

5

Besides the above-mentioned special absorption properties of quinones, the high efficiency in the photoinduced immobilization of ligands observed in this invention, can in part be explained by the fact that the
10 reactive state of the quinone ($n\pi^*$) is obtained in a very high yield upon excitation in the whole absorption range.

Normally incoherent continuous light will be chosen to activate the photoprobes. But the application of more
15 complicated light sources such as monochromatic, polarized, pulsed or coherent light can be used.

In the examples described later on, a HPA lamp from Philips was used as light emitting source. Such HPA lamps
20 are tubular medium-pressure metal halide lamps with iron and cobalt additives.

The lamps emit non-ionizing UV-light from 250 to 400 nm (corresponding to long-wave UV-A and UV-B, mainly 300-400
25 nm), and visible light from 400 to 700 nm, which makes the lamps suitable for use in the present method.

Irradiation times are selected in order to obtain a sufficient yield without degrading the immobilized
30 ligand (L) or the carbon-containing material surface (P). The irradiation time is generally shorter than 12 hours, preferably less than 200 minutes, more preferably less than 60 minutes, most preferably less than 30 minutes.

35

Ligands

A ligand (L) is defined as a surface modifying compound which after immobilization to the polymer surface provides the polymer surface with a new surface characteristic.

The ligand (L) can be a functional group such as:

- 10 -COOH (carboxylic acids), sulfonic acid derivatives, -COOR (esters, including active esters), -COX (acid halides, acid fluorides and acid chlorides, acid azides or similar active carboxylic acid derivatives), -CONHNH₂ (acid hydrazides), -NHCONHNH₂ (semicarbazides),
15 -NHCSNHNH₂ (thiosemicarbazides), -CN (nitriles), -CHO (aldehydes), RR'CO (ketons), -OH (alcohols), -SH (thiols), -SSR (disulfides), -NH₂ (amines, including primary, secondary and tertiary amines), -NHNH₂ (hydrazines), -OR (ethers), epoxides, -SR (sulfides), -X
20 (halides: fluoride, chloride, bromide, or iodide), -NO₂, -CH₃. Also, the ligand can be a biologically active molecule, such as biotin, toxins, herbicides, pesticides, carbohydrates, antibiotics (e.g. penicillins and other drugs, e.g. cell poisons), steroids, peptides,
25 nucleotides, peptide nucleic acids (PNA) and nucleic acid binding partners, proteins and haptens, functional groups (or derivatives thereof) or non-functional groups, such as methyl, ethyl, isobutyl, tertbutyl or aromates. These non-functional groups may e.g. be used to improve
30 the biocompatibility of contact lenses, implants, etc.

Spacer

- The spacers (S₁) or (S) are generally chosen with respect to length, flexibility, hydrophobic/hydrophilic character for each specific new surface characteristic.

The spacer (S_1) or (S) is as a thermochemically or photochemically non-active distance making compound.

- 5 Optionally, the ligand is linked to the polymer surfaces via a spacer, the only function of which is to make space between the two and thereby make the immobilization easier, particularly when the ligand is a large molecule. The spacer also provides for more ligands to be
10 immobilized on the polymer surface.

- The length of the spacer is selected for the specific purpose. Generally, the length is less than or about 400 Å. In some applications, preferably less than about 100
15 Å. In case of longer lengths of the spacer it is preferred to link more ligands to each spacer unit.

- The spacer is also selected with respect to its hydrophobic/hydrophilic character. If e.g. the spacer
20 links the quinone to the ligand before the photoreaction to the polymer, it is very important to optimize the hydrophobic/hydrophilic character of the total Q-S-L molecule in order to obtain optimal reaction conditions also depending on the solvent in the photoreactive step.

- 25 Examples of spacers are C_1 - C_{20} alkyl groups, e.g. polymethylene, optionally containing aromatic or mono-/polyunsaturated hydrocarbons, polyoxyethylene such as polyethylene glycol, oligo/polyamides such as poly- β -alanine, polyglycine, polylysine, peptides in general,
30 etc., oligosaccharides, oligo/polyphosphates such as phospho-mono/diesters, mono/diamides, etc., oligo/poly-sulfonic amides/esters. Moreover, the spacer may consist of combined units of the aforementioned or combined units
35 thereof.

The importance of optimizing the spacer length and other properties are clearly illustrated in example 3 in which the photochemical grafting of primary amino groups is detected by the following thermochemical coupling of biotin and detection of the immobilized biotin with avidin. In this example a stepwise elongation of the spacer with β -alanine units was used. The oligoamide nature of the spacer allowed the easy synthesis of each compound using standard amide bond forming reactions and standard protecting group and deprotection schemes. In contrast to e.g. a simple aliphatic carbon spacer the oligoamide spacer is rather rigid due to the hindered rotation around the amide bonds and rather hydrophilic - but neutral - due to the ability of each amide bond to act both as donor and acceptor of hydrogen bonds. The optimum spacer length for this particular purpose was found to be anthraquinone amine compound 9. Increasing the spacer length with one more β -alanine unit did not increase the signal, but indicated a small decrease of signal (data not shown). This optimization of the spacer length for the biotin-avidin system is consistent with reports in the literature (see e.g. F. Kohnen et al., Complementary Immunoassays, page 62 (W.P. Collins ed.) John Wiley & Sons, New York, 1988).

25

Thermochemical Reactive Groups

Thermochemical reactive groups (T) are well-known in the art and are defined as functional groups, which are able to form covalent bonds to polymer surfaces (P) or ligands (L) under conditions in which the photochemically reactive group is non-reactive.

The thermochemical reactive groups may be -COOH (carboxylic acids), sulfonic acid derivatives, -COOR (esters, comprising active esters), -COX (acid halides,

acid azides and similar carboxylic acid derivatives), -CONHNH₂ (acid hydrazides), -NHCONHNH₂ (semicarbazides), -NHCSNHNH₂ (thiosemicarbazides), -CHO (aldehydes), RR'CO (ketones), -OH (alcohols), -X (halides: chloride, bromide, iodide), -SH (thiols), -SSR (disulfides), -NH₂ (amines, comprising primary, secondary and tertiary amines), -NHNH₂ (hydrazines), epoxides, maleimides.

One of the major advantages in this invention is the chemical stability of the quinone compounds. Thus, thermochemically reactive groups will not react with the quinones.

This is illustrated in synthesis of antraquinone acid hydrazide (compound 12, example 1) and antraquinone thiosemicarbazide (compound 15, example 1). Using benzophenones as the photochemically reactive group, the synthesis of such compounds would be impossible, as the acid hydrazide or thiosemicarbazide would condensate with the carbonyl group in the benzophenone, giving either cyclic compounds or oligomers.

Carbon-containing Material Surface

It is preferred that the carbon-containing material surface is a polymer surface.

The polymer may be any kind of polymer. Particularly preferred polymers are selected from the group consisting of: synthetic and natural polymers such as polystyrene, polyethylene, polyvinylacetate, polyvinylchloride, polyvinylpyrrolidone, polyacrylonitrile, polymethylmethacrylate, polytetrafluoroethylene, polycarbonate, poly-4-methylpentylene, polyester, polypropylene, cellulose, nitrocellulose, starch, polysaccharides,

natural rubber, butyl rubber, styrene butadiene rubber, silicone rubber.

Also, the carbon-containing material can be selected from the group consisting of: premodified materials including silica, glass, control-led pore glass, silica gel, or metal which materials have been premodified to contain carbon; monolayer or multilayer films; Langmuir-Blodgett-films; micelles; biological membranes; proteins; nucleotides, peptide nucleic acids (PNA) and nucleic acid binding partners, natural or synthetic polymers coated with biological or organic material.

The polymer surfaces may e.g. be premodified by e.g. a corona treatment, a treatment of γ -lightening and silylation. Such treatment may enhance the reactiveness of the polymer and/or modify the hydrophobic or hydrophilic character of the surface.

The carbon-containing material may also be a silica, a glass, a controlled pore glass and a silica gel, or a metal which has been premodified to contain carbon, e.g. by silylation so as to make the surface able to form covalent bonds to other compounds, i.e. a quinone compound or a thermochemically reactive compound.

In the following the carbon-containing material surface is described as the "polymer surface" or "substrate". However, it is to be understood that the above-mentioned non-polymer surfaces may be treated as well.

Preferred Methods of Preparation

Preferred methods of carrying out the invention are defined in claims 11-16, wherein the respective compounds are linked to each other in a number of different ways.

A person skilled in the art will know that the method can be carried out in many other ways within the scope of the invention.

5

Preferred and illustrative embodiments (a)-(f) of the invention comprise the following reaction steps:

- 10 a) Step 1: $Q + L \rightarrow Q-L$
 Step 2: $Q-L + P \rightarrow P-Q-L$ (Photoreactive step)
- 15 b) Step 1: $Q + S \rightarrow Q-S$
 Step 2: $Q-S + L \rightarrow Q-S-L$
 Step 3: $Q-S-L + P \rightarrow P-Q-S-L$ (Photoreactive step)
- 20 c) Step 1: $P + Q \rightarrow P-Q$ (Photoreactive step)
 Step 2: $P-Q + L \rightarrow P-Q-L$
- 20 d) Step 1: $P + S_1 \rightarrow P-S_1$
 Step 2: $P-S_1 + Q \rightarrow P-S_1-Q$ (Photoreactive step)
 Step 3: $P-S_1-Q + L \rightarrow P-S_1-Q-L$
- 25 e) Step 1: $Q + T \rightarrow Q-T$
 Step 2: $Q-T + P \rightarrow P-Q-T$ (Photoreactive step)
 Step 3: $P-Q-T + L \rightarrow P-Q-T-L$
- 30 f) Step 1: $Q+S \rightarrow Q-S$
 Step 2: $Q-S + T \rightarrow Q-S-T$
 Step 3: $Q-S-T + P \rightarrow P-Q-S-T$ (Photoreactive step)
 Step 4: $P-Q-S-T + L \rightarrow P-Q-S-T-L$

In embodiment (f) the reaction order of S and T may be reversed in the steps 1 and 2.

35

Photoreactive step

5 The photoreactive step can be carried out as described under Examples, and the thermochemical reactions can be carried out using standard synthetic procedures as known to a person skilled in the art.

Quinone-Ligand Linking

10

Q may be linked to L by any synthetic methods of linking similar compounds. The bond obtained is preferably a covalent bond such as a C-C bond, a bond through acid derivatives (e.g. ester, amide, etc.), an ether bond, an amine, a sulfide or a disulfide bond. The reaction is carried out in a suitable solvent. After completed reaction, the solvent may be removed by e.g. evaporation, decantation or filtration, or the solvent may be replaced by another solvent which is more suitable for the following photoreaction, where Q-L is linked to P. This reaction is preferably carried out in an aqueous solvent, where Q-L is brought into contact with P. The ligand L may have to be protected with one or more protecting groups during the photoreaction. The protecting groups can be selected so as to mask the sensitive functionalities of the ligand during the photochemical step, and so that the ligand can become unmasked in a subsequent step after the photoimmobilization.

20 25 30 The solvent is optimally the same in all steps of coupling of the compounds.

Covalent Bonding

35 The reaction involved in forming the covalent bonds may be selected among the standard synthetic procedures known

to a skilled person, e.g. standard organic synthesis, peptide synthesis, oligonucleotide synthesis and related areas. When using intermediates having multiple functional groups suitable semipermanent and/or transient protecting groups can be chosen to mask selected functional groups, thereby allowing regioselective synthesis of the Q-L and Q-S-L molecule. For well known techniques of protecting functionalities see T.W. Greene and P.G.M. Wuts, "Protective Groups in Organic Synthesis", John Wiley & Sons, New York, 1991.

Illustrative synthesis of Q-L and Q-S-L molecules, including selection of bond forming reactions and selection of suitable protective groups are illustrated in example 1.

Solvent

The solvent used in the photochemical step is preferably an aqueous medium or an aqueous medium containing up to 10% v/v of organic solvent, preferably up to 5% v/v of organic solvent. Neat organic solvent such as tetrachloromethane and benzene may be used. However, some organic solvent may cause problems because of its reactivity with e.g. the excited quinone. Also, organic solvents are more expensive and may result in environmental problems.

The solution in contact with the polymer is then exposed to light and irradiation is performed, optionally for a period up to 200 minutes, typically for less than 60 minutes, preferably less than 30 minutes. This modification does not change the physical properties of the polymer (stability, strenght, transparency, etc.). The solution, preferably an aqueous solution, in which the covalent coupling takes place, is often buffered. This is done to keep defined pH during the reaction and to secure

that certain groups are ionic. The pH value is preferably in the range from 0 - 7 or in the range 7 - 12. The optimal pH value is highly dependent on the specific reaction and the compounds involved. When amines are coupled, the pH is preferably less than 8 to protonate the amino functionality. By doing this, the reagent will be readily soluble in water and together with the quinone in the other part of the compound, the reagent as a whole acts as a soap. This means that the lipophilic quinone part will stick to the polymer, and the polar amino group will point out in the solvent. When e.g. carboxy groups are to be immobilized, the pH will preferably be more than 6 to obtain the same effect. When using aqueous systems, this differential polarity of the reagent as a whole is important in the photochemical immobilization.

Further Advantages

Contrary to benzophenones, the special redox properties of quinones, enables overall reduced quinones which can be formed during photolysis and which are not covalently linked to the surface to be "recycled" as illustrated in Fig. 3.

This recycling system increases the efficiency of the overall photochemical coupling. The high efficiency of the method according to the invention and the surprising findings that quinone-ligand conjugates can be photochemically immobilized on different polymers can be partly explained by this interesting recycling and "conservation" of photoprobes (the photochemical compounds which are to be subjected to a photochemical reaction).

As mentioned above, excited quinones react in radical reactions. The initial step is in general hydrogen atom

abstraction and the rate of reaction is determined by the bond energy of the covalent bond between the hydrogen and the carbon to which it is bonded. This reaction mechanism has the consequence that the exited quinones are not able to react with water which has about the strongest binding of hydrogen atoms. Therefore, by using water as the solvent it is possible to generate extremely reactive species which are not able to react with the solvent.

10 Preferred Uses

Preferred uses of the carbon-containing material as prepared according to the method of this invention comprise use in a detection system, use as carrier for solid phase immuno assays, particularly as well as plates, test particles such as beads and micro spheres, test tubes, test sticks, and test strips, and use as a carrier for solid phase synthesis of peptides, oligonucleotides, carbohydrates and small organic molecules.

3. BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 shows illustrations of applicable basic quinone compounds (I)-(XXXVI) according to the invention.

Fig. 2 shows particularly preferred quinones (XXXVII)-(XXXIX) according to the invention.

Fig. 3 shows an illustration of recycling of reduced quinones.

Fig. 4 illustrates the photochemical reaction of arylazides.

Fig. 5 illustrates the photochemical reaction of benzophenone.

Fig. 6 illustrates photochemical properties of quinones
5 of this invention.

Fig. 7 shows quinone-ligand, quinone-spacer-ligand compounds nos. 1-22 prepared in example 1.

10 Fig. 8a shows a UV grafting of phenanthrene quinone amine compound no. 3 onto polystyrene surfaces (PolySorp®). Effect of photoprobe concentration and irradiation time.
◇ No UV irradiation (control); □ 5 min. irradiation; Δ 7 min.; ○ 10 min.

15 Fig. 8B shows a grafting of phenanthrene quinone amine compound no. 3 onto polystyrene surfaces (Nuncloⁿ Delta treated). Effect of photoprobe concentration and irradiation time. ◇ No. UV irradiation (control); □ 5
20 min. irradiation; Δ 7 min.; ○ 10 min.

Fig. 9a shows a grafting of anthraquinone amine compound no. 5 onto polystyrene surfaces (PolySorp®). Effect of photoprobe concentration and irradiation time. ◇ No. UV
25 irradiation (control); □ 5 min. irradiation; Δ 7 min.; ○ 10 min.

Fig. 9b shows a UV grafting of anthraquinone amine compound no. 5 onto polystyrene surfaces (Nuncloⁿ Delta treated). Effect of photoprobe concentration and
30 irradiation time. ◇ No. UV irradiation (control); □ 5 min. irradiation; Δ 7 min.; ○ 10 min.

Fig. 10 shows a UV grafting of anthraquinone amines
35 compounds nos. 5, 7 and 9 onto polystyrene surfaces. Effect of spacer arm length on signal strength. Open

symbols: results on Nunclon® Delta treated surfaces; closed symbols: results on PolySorp plates. O/● Amine 5, □/■ Amine 7; Δ/▲ Amine 9.

5 Fig. 11 shows the storage stability of anthraquinone amine compound no. 9 UV grafted onto Nunclon® Delta treated polystyrene surfaces. Values are given relative to day zero. O Storage temperature 4 °C; Δ 20 °C; □ 37 °C; ◇ 60 °C.

10

Fig. 12 shows the storage stability of anthraquinone amine compound no. 9 UV grafted onto PolySorp® polystyrene surfaces. Values are given relative to day zero. O Storage temperature 4 °C; Δ 20 °C; □ 37 °C; ◇ 60 °C.

15

Fig. 13 shows the UV grafting of anthraquinone carboxylic acid derivative compound no. 13 onto polystyrene surfaces. Open symbols: results with no UV irradiation (control); closed symbols: results after 10 min. UV irradiation. O/● PolySorp® plates; Δ/▲ Nunclon® Delta treated plates.

20

Fig. 14 shows a UV grafting of peptide compound no. 19, N-terminally anthraquinone substituted, onto polystyrene surfaces: Effect of irradiation time and concentration of Hyb 161-2 anti peptide monoclonal antibody. 2 min. irradiation; ● 5 min.; Δ 10 min.; ▲ 15 min.; □ 30 min.; ■ 60 min.

30

Fig. 15 shows a UV grafting of anthraquinone peptide compound no. 19 onto polystyrene surfaces. Effect of irradiation time with a constant concentration of Hyb 161-2 anti peptide monoclonal antibody. O Non specific binding with no Hyb 161-2 added; ● Hyb 161-2 added (1 mg/ml).

35

Fig. 16 shows a UV grafting of peptide compound no. 19, N-terminally anthraquinone substituted, onto polystyrene surfaces. Effect of peptide concentration. Closed symbols: 10 min. irradiation time; open symbols: no irradiation. O/● Anthraquinone-peptide 9; Δ/▲ unsubstituted peptide.

Fig. 17 shows the storage stability of UV grafted peptide compound no. 19. O Storage temperature 37 °C; ● 4 °C.

Fig. 18a shows UV grafting of anthraquinone NTA derivative 20 onto polystyrene surfaces. Effect of photoprobe concentration. Open symbols: results with no UV irradiation (control); closed symbols: results after 5 min UV irradiation.

Fig. 18b shows binding of a biotinylated histidine tagged peptide onto NTA modified polystyrene surfaces. 1: no peptide added (control); 2: binding of biotinylated non-histidine tagged peptide biotin-εAhx-Leu-Lys-Leu-Lys-Trp-Lys-OH (control); 3: binding of biotinylated histidine tagged peptide biotin-εAhx-Leu-Lys-Leu-Lys-Trp-Lys-His-His-His-His-His-OH; 4: binding of biotinylated non-histidine tagged peptide biotin-εAhx-Arg-Thr-Gln-Asp-Glu-Asn-Pro-Val-Val-His-Phe-Lys-Asn-Ile-Val-Thr-Pro-Arg-Thr-Pro-OH (control).

Fig. 19 shows UV grafting of the anthraquinone PEG2000 derivative 22 onto polystyrene surfaces. PS063: 0.3 mM photoprobe, 5 min UV irradiation; PS064: 0.3 mM photoprobe, no UV irradiation (control); PS065: 0.3 mM PEG2000, 5 min UV irradiation (control); PS066: 0.3 mM PEG2000, no UV irradiation (control); PS067: H₂O alone, 5 min UV irradiation (control); PS068: H₂O alone, no UV irradiation (control).

Fig. 20 shows UV grafting of the anthraquinone PEG2000 derivative 22 onto polypropylene surfaces. PP011: 0.3 mM photoprobe, 5 min UV irradiation; PP012: 0.3 mM photoprobe, no UV irradiation (control); PP013: H₂O alone, no UV irradiation (control).

4. DETAILED DESCRIPTION

10 Prior art - photochemical reaction of arylazides

The photochemical reaction of the arylazides and derivatives thereof is illustrated in Fig. 4. Nu-H is e.g. H₂O, R-OH, R-SH, R-NH₂ or "polymer". When irradiated with high energy UV light, i.e. as in Table 1 in example 2, a very reactive nitrene is formed and is quickly rearranged to a dehydroazepine. The latter is extremely unstable and will immediately react with the first nucleophilic compound it meets. If this is the solvent, e.g. water, the photoreagent is lost and no reaction is performed with the polymer. When using such reagents, it is therefore necessary that the surface is preincubated with the photoreagent, whereafter the redundant of the reagent is removed and the surface dried prior to the photolysis. When introducing strongly electron withdrawing groups the photochemical mechanism can be changed to nitrene photochemical reaction, but the nitrene compound will also react with the solvent, including water. Combined with long irradiation times (typically 12 hours), this makes the application of this photoreactive group time-consuming and inefficient.

Prior art - photochemical reaction of ketones

35 The major drawback of photochemical reactive ketones is their photochemical oxidation to the corresponding alcohol

resulting in loss of the photochemical reagent. Also, they require long irradiation times of typically 12 hours which makes them unsuitable for immobilization of sensitive biomolecules.

5

Prior art - photochemical reaction of benzophenone

The photochemistry of benzophenones results in the formation of a C-C bonding contrary to quinones which
10 forms an ether bonding. Both groups have the advantage of not being reactive with water. Therefore, water can be used as a solvent.

The photochemical reaction of benzophenone and deriva-
15 tives thereof is illustrated in Fig. 5, wherein R designates the polymer.

Such a photoreactive group based on benzophenone forms a radical by excitation with high energy UV light followed
20 by hydrogen atom abstraction from a substrate, which radical either combines with the formed substrate radical to the product or which radical abstracts another hydrogen atom from a substrate, which results in a photochemical reduction to the corresponding alcohol with
25 consequent loss of the photoreagent. Substrates for these reactions are organic molecules, including synthetic polymers, but also organic solvents such as e.g. alcohols.

30 The photochemical coupling typically requires irradiation at 320 nm for 12 hours to obtain an effective coupling to the polymer.

35

Photochemical Properties of Quinones of this Invention

The excited quinone reacts in general as a free radical and results in addition to double/triple bonds, abstracts
5 hydrogen atoms, initiates chain reactions, etc. Due to the resonance configuration of the quinone, the radical reaction can take place on both or all the carbonyl groups of the quinone as illustrated in Fig. 6.

10 These reaction patterns are the fundamental photochemical properties of the quinones in this invention. Due to their general behaviour most quinones will be able to perform this kind of chemistry.

15 5. EXAMPLES

In the following the invention is further described by reference to a number of specific examples.

20	AQ:	anthraquinone
	BOP:	benzotriazole-1-yl-N-oxytris-(dimethylamino)- phosphonium hexafluorophosphate
	But:	tert-butyl
	DCC:	dicyclohexylcarbodiimide
25	DCU:	dicyclohexyl urea
	DIEA:	diisopropylethylamine
	DMF:	dimethylformamide
	DMSO:	dimethylsulfoxide
	EI:	electron ionization
30	ELISA:	enzyme linked immunosorbent assay
	FAB:	fast atom bombardment
	Fmoc:	fluorenylmethoxycarbonyl
	HPLC:	high performance liquid chromatography
	Mp:	melting poing
35	MS:	mass spectrometry
	NMR:	nuclear magnetic resonance

NTA: N-nitrilotriacetic acid
OPD: phenylene-1,2-diamine dihydrochloride
PEG: polyethylene glycol
Pmc: 2,2,5,7,8 pentamethylchroman-6-sulfonyl
5 TFA: trifluoroacetic acid
THF: tetrahydrofuran
TLC: thin layer chromatography

EXAMPLE 1

10

Fig. 7 shows quinone-ligand, quinone-spacer-ligand compounds nos. 1-22 which have been synthesized as described in the following.

15

The mono-Boc-protected diamines were prepared as described by Krapcho and Kuell, Synthetic Communications 1990, 20, 2559-2564.

3-Carboxy-phenanthrenequinone (compound no. 1)

20

3-Acetylphenanthrene (5 g, 0.23 mmol) was dissolved in warm acetic acid (100 ml, 60 °C) and chrom(VI)oxide (30 g, 0.6 mol) was added in small portions. During this the temperature rose to the boiling point. After addition of
25 all chrom(VI)oxide the solution was diluted with water (500 ml) and the precipitate was filtered off, washed with acetic acid/H₂O (1:1), cold acetic acid and finally with diethyl ether. Yield: 2.1 g (37% from 3-acetylphenanthrene); Mp: 280 °C.

30

MS (EI): 252 (M⁺).

¹H NMR (d₆-DMSO): 8.70 ppm (s, 1H), 8.34 (d, 1H), 8.08 (m, 3H), 7.80 (t, 1H), 7.57 (t, 1H).

35

N-(3-Boc-aminopropyl)-phenanthrenequinone-3-carboxamide
(compound no. 2)

Compound no. 1 (250 mg, 1.0 mmol), DCC (245 mg, 1.2 mmol)
5 and HODhbt (178 mg, 1.1 mmol) were dissolved in dioxane
(50 ml), and the mixture was allowed to react overnight.
The dioxane was evaporated in vacuo, and the residue was
suspended in DMF (25 ml). Mono-Boc-1,3-propanediamine •
HCl (333 mg, 1.2 mmol) was added to the suspension
10 followed by excess triethylamine (1 ml). After 1 hour DCU
was filtered off and water (150 ml) was added. The yellow
precipitate was collected by filtration and the product
recrystallized from ethyl acetate. Yield: 0.235 mg (56%
from compound no. 1); Mp: 195 °C (dec.).

15 ¹H NMR (CDCl₃): 8.02 ppm (t, 1H), 7.98 (s, 1H), 7.65 (d,
1H), 7.51-7.45 (m, 2H), 7.33 (d, 1H), 7.14 (t, 1H), 6.89
(t, 1H), 5.62 (b, 1H), 2.89-2.71 (m, 2H), 2.44-2.41 (m,
2H), 1.11-0.75 (m, 11H).

20 N-(3-Aminopropyl)-phenanthrenequinone-3-carboxamide • HCl
(compound no. 3)

Compound no. 2 (100 mg, 0.24 mmol) was dissolved in
25 slightly warmed acetic acid (2.5 ml, 50 °C), and 1 M HCl
in acetic acid was added (2.5 ml). After 5 minutes ether
was added (10 ml), and the precipitate was collected by
filtration and was washed several times with ether.
Yield: 81 mg (95% from compound no. 2).

30 ¹H NMR (d₆-DMSO): 9.20 ppm (b, 1H), 8.78 (s, 1H), 8.54
(d, 1H), 8.14-7.99 (m, 6H), 7.86 (t, 1H), 7.60 (t, 1H),
3.38 (-CH₂-N-R), 2.88 (b, 2H), 1.69 (s, 2H).

35 UV (ethanol/water): λ_{max} = 266 nm (ε = 39000), 330
(5700), 424 (1400).

5

N-(3-Boc-aminopropyl)-anthraquinone-2-carboxamide
(compound no. 4)

Anthraquinone-2-carboxylic acid (2.52 g 10 mmol) was
10 suspended in dry THF (100 ml). The suspension was cooled
to 0 °C, and DCC (2.06 g, 10 mmol) was added, and the
mixture stirred for 5 minutes. Solid HODhbt (1.63 g, 10
mmol) was added, and the mixture stirred for 10 minutes
at 0 °C and then at room temperature overnight. THF was
15 removed in vacuo (40 °C), and the solid residue was
resuspended in DMF (100 ml). Mono-Boc-1,3-propanediamine
• HCl (4.21 g, 20 mmol) was added to the suspension
followed by excess triethylamine (7 ml). After 2 h DCU
was removed by filtration and water (200 ml) was added.
20 The yellow precipitate was collected by filtration and
the product recrystallized from ethyl acetate (200 ml).
Yield: 3.53 g (87% from anthraquinone-2-carboxylic acid);
Mp: 173-175 °C; TLC (ethyl acetate): R_f = 0.61.
MS (FAB⁺): 409.1 (MH⁺).

25

¹H NMR (d₆-DMSO): 9.00 ppm (t, 1H), 8.75 (s, 1H), 8.40
(dd, 1H), 8.30 (m, 3H), 8.05 (m, 2H), 6.90 (t, 1H), 3.40
(q, 2H), 3.10 (q, 2H), 1.80 (qn, 2H), 1.45 (s, 9H).

30 N-(3-Aminopropyl)-anthraquinone-2-carboxamide • HCl
(compound no. 5)

Compound no. 4 (5.92 g, 14.5 mmol) was suspended in
methanol (200 ml). 6 M HCl in methanol (15 ml) was added,
35 and the mixture was heated to reflux for 1 hour. The
mixture was cooled to 0 °C, and diethyl ether (200 ml)

was added. The precipitated product was collected by filtration and washed several times with ether. Yield: 3.98 g (80% from compound no. 4); Mp: 250 °C (dec.); TLC (1-butanol/acetic acid/water 4:1:1): R_f = 0.43.

5 MS (FAB⁺): 309.1 (MH⁺).

¹H NMR (d₆-DMSO): 9.00 ppm (t, 1H), 8.75 (s, 1H), 8.50 (dd, 1H), 8.30 (m, 3H), 8.15 (s, 3H), 8.10 (m, 2H), 3.50 (q, 2H), 2.95 (t, 2H), 1.95 (qn, 2H).

10 UV (ethanol/water): λ_{max} = 256 nm (ϵ = 49000), 332 (4700), 390 (310).

Boc- β -Ala-NH-(CH₂)₃-NHCO-AO (compound no. 6)

15 Boc- β -Ala-OH (0.605 g, 3.20 mmol) and BOP (1.283 g, 2.9 mmol) were dissolved in DMF (50 ml), and triethylamine (4 ml, 30 mmol) was added. The mixture was allowed to preactivate for 5 minutes before compound no. 5 (1.00 g, 2.90 mmol) was added in one portion. The reaction mixture
20 was stirred at room temperature overnight, and the product was precipitated by the addition of water (50 ml). The crude product was filtered off, washed several times with water, and finally recrystallized from ethanol/water. Yield: 1.40 g (92% from compound no. 5);
25 Mp: 178-179 °C, TLC (ethyl acetate/methanol/acetic acid 85:10:5): R_f = 0.73. MS (FAB⁺): 480.2 (MH⁺).

¹H NMR (d₆-DMSO): 9.00 ppm (t, 1H), 8.75 (s, 1H), 8.40 (dd, 1H), 8.35 (m, 3H), 8.05 (m, 2H), 7.90 (t, 1H), 6.80
30 (t, 1H), 3.40 (q, 2H), 3.20 (q, 4H), 2.30 (t, 2H), 1.75 (qn, 2H), 1.45 (s, 9H).

H- β -Ala-NH-(CH₂)₃-NHCO-AO • HCl (Compound no. 7)

35 Compound no. 6 (0.220 g 2.54 mmol) was suspended in methanol (40 ml). 6 M HCl in methanol (5 ml) was added,

and the mixture was heated to reflux for 1 hour. The mixture was cooled to 0 °C, and diethyl ether (40 ml) was added. The precipitated product was collected by filtration and washed several times with ether. Yield: 0.970 g (92% from compound no. 6); Mp: 219 °C (dec.); TLC (1-butanol/acetic acid/water 4:1:1): R_f : 0.40. MS (FAB⁺): 380.1 (MH⁺).

¹H NMR (d₆-DMSO): 9.10 ppm (t, 1H), 8.75 (s, 1H), 8.45 (dd, 1H), 8.35 (m, 4H), 8.15 (s, 3H), 8.10 (m, 2H), 3.45 (m, 4H), 3.25 (q, 2H), 3.10 (t, 2H), 1.80 (q, 2H).

Boc-βAla-βAla-NH-(CH₂)₃-NHCO-AO (compound no. 8)

15

Compound no. 7 (0.492 g, 2.60 mmol) and BOP (0.955 g, 2.16 mmol) were dissolved in DMF (80 ml), and triethylamine (1.5 ml, 10.8 mmol) was added. The mixture was allowed to preactivate for 5 minutes before compound no. 7 (0.900 g, 2.16 mmol) was added in one portion. The reaction mixture was stirred at room temperature overnight, and the product was precipitated by the addition of water (80 ml). The crude product was filtered off, washed several times with water, and finally recrystallized from ethanol/water. Yield: 0.740 g (62% from compound no. 7); Mp: 183-184 °C; TLC (ethyl acetate/methanol/acetic acid 85:10:5): R_f = 0.45. MS (FAB⁺): 551.3 (MH⁺).

¹H NMR (d₆-DMSO): 9.05 ppm (t, 1H), 8.75 (s, 1H), 8.30 (m, 4H), 8.10 (m, 2H), 7.90 (dt, 2H), 6.75 (t, 1H), 3.40 (q, 2H), 3.35 (q, 2H), 3.20 (dq, 4H), 2.30 (dt, 4H), 1.80 (qn, 2H), 1.45 (s, 9H).

35

H- β Ala- β Ala-NH-(CH₂)₃-NHCO-AO • HCl (compound no. 9)

Compound no. 8 (0.740 g, 1.35 mmol) was suspended in methanol (15 ml). 6 M HCl in methanol (1 ml) was added, and the mixture was heated to reflux for 1 hour. The mixture was cooled to 0 °C, and diethyl ether (15 ml) was added. The precipitated product was collected by filtration and washed several times with ether. Yield: 0.591 g (90% from compound no. 6); Mp: 216-219 °C; TLC (1-butanol/acetic acid/water 4:1:1): R_f = 0.26. MS (FAB⁺): 451.1 (MH⁺).

¹H NMR (d₆-DMSO): 9.00 ppm (t, 1H), 8.60 (d, 1H), 8.35 (dd, 1H), 8.30 (d, 1H), 8.25 (m, 2H), 8.15 (t, 1H), 7.95 (m, 3H), 7.80 (s, 3H), 3.30 (m, 6H), 3.15 (q, 2H), 2.50 (t, 2H), 2.30 (t, 2H), 1.75 (qn, 2H).

Boc- β Ala- β Ala- β Ala-NH-(CH₂)₃-NHCO-AO (compound no. 10)

Compound no. 9 (0.263 g, 1.39 mmol) and BOP (0.513 g, 1.16 mmol) were dissolved in DMF (50 ml), and diisopropylethyl amine (2 ml, 12 mmol) was added. The mixture was allowed to preactivate for 5 minutes before compound no. 9 (0.564 g, 1.16 mmol) was added in one portion. The reaction mixture was stirred at room temperature overnight, and the product was precipitated by the addition of water (50 ml). The crude product was filtered off, washed several times with water, and finally recrystallized from ethanol/water. Yield: 0.654 g (91% from compound no. 9); Mp: 209-213 °C; TLC (methanol): R_f = 0.60. MS (FAB⁺): 622.2 (MH⁺).

¹H NMR (d₆-DMSO): 9.05 ppm (t, 1H), 8.75 (s, 1H), 8.30 (m, 4H), 8.10 (m, 2H), 8.00 (dt, 2H), 7.90 (t, 1H), 6.80 (t, 1H), 3.30 (dq, 6H), 3.20 (dq, 4H), 2.30 (tt, 6H), 1.80 (qn, 2H), 1.45 (s, 9H).

H- β Ala- β Ala- β Ala-NH-(CH₂)₃-NHCO-AO • HCl (compound no. 11)

5 Compound no. 10 (0.500 g, 0.800 mmol) was suspended in methanol (15 ml). 6 M HCl in methanol (1 ml) was added, and the mixture was heated to reflux for 1 hour. The mixture was cooled to 0 °C, and diethyl ether (15 ml) was added. The precipitated product was collected by
10 filtration and washed several times with ether. Yield: 0.400 g (89% from compound no. 10); Mp: 235-237 °C (dec.); TLC: (1-butanol/acetic acid/water 4:1:1): R_f = 0.14. MS (FAB⁺): 522.1 (MH⁺).

15 ¹H NMR (d₆-DMSO): 9.00 ppm (t, 1H), 8.65 (d, 1H), 8.30 (d, 1H), 8.25 (m, 2H), 8.15 (t, 1H), 8.00 (m, 2H), 7.90 (s, 3H), 3.35 (t, 2H), 3.25 (q, 4H), 3.15 (q, 2H), 2.95 (q, 2H), 2.50 (t, 2H), 2.30 (dt, 4H), 1.70 (qn, 2H).

20 N-(5-carboxymethyl-pentyl)anthraquinone-2-carboxamide (compound no. 12)

Anthraquinone-2-carboxylic acid (2.52 g, 10 mmol) was suspended in dry THF (100 ml) and cooled to 0 °C. Then,
25 DCC (2.26 g, 11 mmol) was added, and the mixture stirred for 5 minutes. Solid HODhbt (1.63 g, 10 mmol) and the mixture stirred at 0 °C for 10 minutes and then at room temperature overnight. THF was removed in vacuo, and the solid residue was resuspended in DMF (100 ml). 6-
30 Aminohexanoic acid methyl ester • HCl (1.99 g, 11 mmol) followed by triethyl amine (7 ml, 50 mmol) were added, and the mixture stirred at room temperature overnight. DCU was removed by filtration, and the product was precipitated by the addition of water (200 ml). The crude
35 product was collected by filtration and recrystallized from ethyl acetate. Yield: 3.09 g (73% from

anthraquinone-2-carboxylic acid); Mp: 144-145 °C; TLC (ethyl acetate): R_f = 0.68. MS (FAB⁺): 380.1 (MH⁺).

¹H NMR (d₆-DMSO): 9.00 ppm (t, 1H), 8.75 (s, 1H), 8.40 (dd, 1H), 8.30 (m, 3H), 8.05 (m, 2H), 3.70 (s, 3H), 3.40 (q, 2H), 2.40 (t, 2H), 1.70 (qn, 6H), 1.40 (qn, 4H).

N-(5-carboxypentyl)-anthraquinone-2-carboxamide (compound no. 13)

10

Compound no. 12 (0.949 g, 2.5 mmol) was suspended in THF (15 ml). 0.5 M LiOH (15 ml) was added, and the mixture stirred at room temperature for 1 hour. THF was removed in vacuo, and the product was precipitated by the addition of 2 M HCl (6 ml). The crude product was collected by filtration, washed with water and dried in vacuo. Yield: 0.822 g (90% from compound no. 12); Mp: 198-199 °C; TLC (petroleum ether/ethyl acetate/acetic acid 5:5:1): R_f = 0.43. MS (FAB⁺): 366.2 (MH⁺).

20

¹H NMR (d₆-DMSO): 12.00 ppm (s, 1H), 9.00 (t, 1H), 8.75 (s, 1H), 8.40 (dd, 1H), 8.35 (m, 3H), 8.00 (m, 2H), 2.30 (t, 2H), 1.60 (qn, 6H), 1.40 (qn, 4H).

N-(6-hydrazido-hexyl)-anthraquinone-2-carboxamide (compound no. 14)

Compound no. 12 (0.5 g, 1.32 mmol) was suspended in methanol (5 ml). Hydrazine hydrate (1 ml, 20 mmol) was added in one portion, and the reaction mixture was refluxed for 6 h and then allowed to cool to room temperature. The solvent was removed in vacuo, and the remanence was resuspended in ice cold water (20 ml). The precipitated product was collected by filtration and washed with water and dried in vacuo. Yield: 0.373 g (75% from compound no. 12); Mp: 181 °C (dec.); TLC (ethyl

acetate/methanol 6:4): R_f = 0.48. MS (FAB^+): 380.24 (MH^+).

5 1-(3-(carboxamido-anthraquinone-2-yl)-propyl)-thiosemicarbazide (compound 15)

BOP (0.257 g, 0.58 mmol) and carbon disulfide (0.35 ml, 5.8 mmol) was dissolved in DMF. Then, triethyl amine (0.24 ml, 1.74 mmol) followed by solid compound no. 5
10 (0.2 g, 0.58 mmol) was added. The mixture was stirred for 1 hour at room temperature. Excess carbon disulfide was removed in vacuo, and the solution was added dropwise to a stirred ice cold solution of hydrazine hydrate (0.5 ml, 7.8 mmol) in DMF (0.5 ml). The mixture was stirred
15 overnight at room temperature, and the product was precipitated by addition of ice cold water (25 ml). The precipitated product was collected by filtration and washed with water and dried in vacuo. Yield: 0.164 g (74% from compound no. 5); Mp: 202-205 °C (dec.); TLC (ethyl
20 acetate/methanol 6:4): R_f = 0.63. MS (FAB^+): 383.1 (MH^+).

HO₂C-(CH₂)₃-CONH-(CH₂)₃-NHCO-AO (compound no. 16)

25 Compound no. 12 (0.45 g, 1.31 mmol) and maleic anhydride (0.19 g, 1.9 mmol) was dissolved in DMF (30 ml). Triethylamine (1.8 ml, 13.1 mmol) was added, and the mixture was stirred at room temperature for 3 hours. The product was precipitated by the addition of ice cold 0.5
30 M HCl (30 ml), collected by filtration and recrystallized from ethanol/water. Yield: 0.374 g (79% from compound no. 12); TLC (ethyl acetate/methanol 6:4): R_f = 0.33. MS (FAB^+): 409.1 (MH^+).

α -D-Glcp-(1 \rightarrow 4)- β -D-Glcp-1-N(Ac)-(CH₂)₃-NH-CO-AQ
(compound no. 17)

Compound no. 5 (0.103 g, 0.300 mmol) and maltose
5 monohydrate (0.324 mg, 0.900 mmol) were dissolved in dry
methanol. DIEA (70 μ l, 0.400 mmol) was added and the
mixture was heated in nitrogen atmosphere overnight. The
mixture was cooled to 0 °C, and acetic anhydride (1 ml)
10 was added. After standing at room temperature overnight
methanol was removed in vacuo, and the residue was
dissolved in water and filtered through a 0.2 μ m filter
and freeze dried. The resulting solid was redissolved in
water and loaded onto two Sep-Pak Vac cartridges (C₁₈,
100 mg sorbent).

15

Residual free maltose was eluted with water (2 x 10 ml)
and the quinone-maltose conjugate eluted with 50%
acetonitrile/water. The combined acetonitrile/water
fractions were freeze dried to yield compound no. 17 as a
20 slightly yellow voluminous powder. Yield: 0.203 mg (100%
from compound no. 5); TLC: R_f = 0.32 (major spot,
compound no. 17); R_f = 0.66 (minor spot, CH₃-CONH-(CH₂)₃-
NHCO-AQ); HPLC (Delta Pak 5 μ C₁₈ 3.9 x 150 mm; buffer A:
0.1% TFA in H₂O; buffer B: 0.1% TFA in acetonitrile/water
25 9:1; gradient: 100% A for 2 minutes, then a linear
gradient from 100% A to 100% B over 20 minutes, then 100%
B for 5 minutes): Rt = 12.07 minutes (77%, 332 nm), 12.29
(5%), 12.67 (14%), 13.35 (4%, CH₃-CONH-(CH₂)₃-NHCO-AQ).
MS (FAB⁺): 675.25 (MH⁺); 717.48 (MH⁺ + CH₃-CO); 759.58
30 (MH⁺ + 2 CH₃CO); 351.16 (CH₃-CONH-(CH₂)₃-NHCO-AQ • H⁺).

AQ-CO-(CH₂)₃-NH-6-ketoestradiol-6-(O-carboxymethyl)-oxime
(compound no. 18)

35 Compound no. 5 (48 mg, 0.139 mmol), 6-ketoestradiol-6-(O-
carboxymethyl)-oxime (50 mg, 0.139 mmol) and BOP (65 mg,

0.139 mmol) were suspended in DMF. Diisopropylethyl amine (49 μ l, 0.278 mmol) was added and the mixture stirred at room temperature for 3 hours. Water (3 ml) was added, and the precipitated product was filtered off, washed with
5 10% Na_2CO_3 (three times), 10% KHSO_4 (three times), several times with water and finally dried in vacuo. Yield: 90 mg (100%); TLC (ethyl acetate/acetic acid 95:5): R_f = 0.27. MS (FAB⁺): 650.26 (MH⁺); 672.28 (M+Na⁺).

10

AO-CO- ϵ Ahx-Gln-Glu-Ser-Gly-Val-Ser-Gly-Arg-OH (compound no. 19)

H-Gln-Glu(OBu^t)-Ser(bu⁺)-Gly-Val-Ser(bu⁺)-Gly-Arg(Pmc)-
15 PepSyn-KA was synthesized using a standard Fmoc-protocol on a custom-made fully automatic continuous flow peptide synthesizer with solid phase online monitoring of coupling reactions. Fmoc-Arg(Pmc)-PepSyn-KA resin (750 mg, 0.09 mmol/g) was loaded onto a column and each individual coupling was performed with the corresponding Fmoc-amino-acid-OPfp-esters (3 equivalents) and HODhbt (1 equivalent) added as catalyst/indicator except serine which was coupled as the Dhbt-ester. At the end of the synthesis the peptidyl resin was transferred to a bubbler
25 apparatus and N-(5-carboxypentyl)-anthraquinone-2-carboxamide (compound no. 13) (3 equivalents) and BOP (3 equivalents) followed by DIEA (9 equivalents) added to the resin. The coupling was allowed to proceed overnight. The N-terminally quinone substituted peptide was cleaved
30 from the resin with Reagent K (TFA/H₂O/thioanisole/phenol/ethane diethiol 82.5:5:5:2.5). The resin was filtered off on a sintered glass filter, washed several times with TFA, and the cleavage mixture concentrated in a stream of nitrogen. The peptide was precipitated with
35 ice cold diethyl ether, and the peptide pellet was redissolved in 2% acetic acid/water, filtered through a

0.2 μ m filter and finally freeze dried. HPLC (Delta Pak 5 μ C₁₈ 3.9 x 150 mm; buffer A: 0.1% TFA in H₂O; buffer B: 0.1% TFA in acetonitrile/ water 9:1; gradient: 100% A for 2 minutes, then a linear gradient from 100% A to 100% B over 20 minutes, then 100% B for 5 minutes): Rt = 13.64 minutes; purity \geq 90% (220 nm). MS (FAB⁺): 1166.35 (MH⁺).

NTA- β Ala- β Ala-NH-(CH₂)₃-NHCO-AO (compound no. 20)

- 10 Glycerine tert.butyl ester \cdot HCl (3.34 g, 20 mmol) was dissolved in aqueous sodium carbonate. The free tert.butyl ester was extracted into dichloro methane (3 x 100 ml) and dried above sodium carbonate. The solvent was removed *in vacuo* giving 2.44 g (92%) of the free
- 15 tert.butyl ester. DIEA (20 ml) was added followed by benzyl-2-bromoacetate (8 ml). The mixture was heated to reflux for 45 min, then cooled to room temperature, diluted with ethyl acetate and washed with aqueous sodium carbonate followed by water. The solvent was removed *in*
- 20 *vacuo* and the NTA-tert-butyl-dibenzyl ester purified on a silicagel column using a gradient of 10-30% ethyl acetate in hexane as eluent. Yield 7.1 g (83%). The tert.butyl ester was cleaved by refluxing for two hours with a 1:1 mixture of TFA and dichloro methane giving NTA-dibenzyl
- 25 ester as the trifluoro acetate.

- Compound no. 9 (0.394 g, 0.809 mmol), NTA-dibenzyl ester (0.383 g, 1.03 mmol) and BOP (0.456 g, 1.03 mmol) was suspended in DMF (20 ml). DIEA (0.87 ml, 5 mmol) was
- 30 added, and the mixture was left overnight. Water was added (20 ml), and the precipitated product was collected by filtration and washed several times with water. The crude product was dissolved in hot ethanol (75 ml), and the solution was decolorised with activated carbon. Water
- 35 was added (50 ml), and the solution was concentrated to approx. 60 ml. The mixture was left overnight at room

temperature, and the precipitated product was filtered off. The solid was suspended in THF (10 ml) and 0.5 M LiOH (5 ml) was added. The solution was stirred at room temperature for 2.5 hour, then THF was removed in vacuo and 10% phosphoric acid added. The product was collected by filtration, washed with water and dried in vacuo. Yield: 0.214 g (42% from compound no. 9); Mp: 158-163 °C; TLC (methanol/pyridine/acetic acid 80:20:6): R_f = 0.42. MS (FAB⁺): 624.23 (MH⁺); 646.20 (M+Na⁺).

10

Anthraquinone-2-carboxylic acid chloride (compound no. 21)

Anthraquinone-2-carboxylic acid (2.52 g, 10 mmol) was suspended in dichloro methane (100 ml). Thionyl chloride (50 ml) was added and the mixture heated to reflux in a nitrogen atmosphere for several hours giving a clear yellow solution. Dichloro methane and excess thionyl chloride was removed in vacuo giving a yellow solid. The solid was filtered off, washed several times with petroleum ether and dried in vacuo. Yield 2.69 g (99% from anthraquinone-2-carboxylic acid); MP: 143-144.5 °C; TLC (analyzed as the methyl ester: a small sample of the acid chloride was dissolved in dry methanol and analyzed immediately using ethyl acetate as eluent); R_f = 0.68. MS (FAB⁺): 307.1 (MH⁺).

20

25

AO-CO-PEG2000 (compound no. 22).

PEG2000 (2.00 g, 1 mmol) was dissolved in toluene (100 ml). 50 ml of the toluene was distilled off and the solution cooled to r.t.. Anthraquinone-2-carboxylic acid chloride (0.271 g, 1 mmol) followed by pyridine (1.6 ml, 20 mmol) was added and the mixture heated to reflux in a nitrogen atmosphere for one hour. Toluene and excess pyridine was removed by distillation, then water (100 ml)

35

was added and residual toluene removed by azeotrope distillation. The target compound was isolated by freeze drying from water. Yield 2.28 g (102%). HPLC (Delta Pak 5 μ C₁₈ 3.9 x 150 mm; buffer A: 0.1% TFA in water; buffer B: 0.1% TFA in acetonitrile/water 9:1; gradient: 25% A + 75% B for 2 minutes, then a linear gradient from 25% + 75% B to 100% B over 10 minutes, then 100% B for 10 minutes; R_t = 2.4 min (anthraquinone-2-carboxylic acid: 2.6% (330 nm)); R_t = 3.69 min (AQ-CO-PEG2000: 78.9% (330 nm)); R_t = 7.08 min (AQ-CO-PEG2000-CO-AQ: 18.5% (330 nm)).

EXAMPLE 2

Compound no. 5 in Example 1 substituted anthraquinone (VII) (in this experiment designated Q1) and compound no. 3 in Example 1 substituted phenanthrenequinone (VIII) (in this experiment designated Q2) and a selected number of other photoprobes were studied for absorbance in the wavelength range from 190-820 nanometers. Compound XXVI correspond to the structure shown in Fig. 1.

The following absorption maxima and extinction coefficient (ϵ) was found (see Table 1).

25

TABLE 1

UV/data of photoprobes (n.a. = no absorption)						
Compound	$\lambda_{\text{max}}(\text{nm})$	$\epsilon_{\text{max}}(\text{M}^{-1}\text{cm}^{-1})$	$\lambda_{\text{max}}(\text{nm})$	$\epsilon_{\text{max}}(\text{M}^{-1}\text{cm}^{-1})$	$\lambda_{\text{max}}(\text{nm})$	$\epsilon_{\text{max}}(\text{M}^{-1}\text{cm}^{-1})$
Azidobenzene	247	7900	315	80	(n.a.)	-
Benzophenone	260	14000	333	110	(n.a.)	-
Anthracenequinone	252	39000	325	4700	390	110
Phenanthrenequinone	266	29000	328	4300	425	1400
Q1	256	49000	332	4700	390	310
Q2	266	39000	330	5700	424	1400
XXVI	253	2500	263	2350	398	69000

EXAMPLE 3Introduction of primary amino groups onto polystyrene surfaces by UV grafting

5

The effect of quinone type as well as the effect of photoprobe concentration and irradiation time on the introduction of primary amino groups were tested with phenanthrene quinone amine compound no. 3 and anthraquinone amine compound no. 5 on two types of polystyrene: 1) Nunc-Immuno[®] Module F16 PolySorp (untreated polystyrene, Nunc cat. no. 467679); 2) non-sterile Nunc F96 Nunclon[®] Delta treated plates). The quinone amines compound no. 3 and compound no. 5 were dissolved in distilled water, and 100 μ l was added to each well of the ELISA plates in a five-fold dilution series with a start concentration of 0.58 μ M of the photoprobes. The plates were placed 14 cm under the UV lamp (Philips HPA 400: the lamp emits low energy UV-A and UV-B light mainly between 300 and 400 nm), and they were irradiated for 5, 7 and 10 minutes, respectively. The wells were rinsed three times with demineralized water and dried for 50 minutes at 60 °C. Plates containing the photoprobes were kept in the dark during photolysis as controls. Biotin-succinimide ester (Sigma cat. no. H 1759) in PBS buffer (phosphate buffered saline: 0.15 M Na⁺, 4.2 mM K⁺, 7.9 mM phosphate, pH 7.2) was added (100 μ l/well), and the wells were allowed to incubate overnight at room temperature. The wells were washed three times with CovaBuffer (PBS buffer pH 7.2 + 2 M NaCl + 4.1 mM MgSO₄ + 0.5% (v/v) Tween 20^R) leaving CovaBuffer (PBS buffer pH 7.2 + 2 M NaCl + 4.1 mM MgSO₄ + 0.5% (v/v) Tween 20^R) leaving CovaBuffer in the wells for 10 minutes after the last wash. The wells were aspirated and avidin mix (4 μ g/ml avidin (Sigma cat. no. A 9390) and 0.13 μ g/ml Horse Radish Peroxidase conjugated avidin (DAKO

cat. no. P 347) in PBS buffer pH 7.2) was added to each well (100 μ l/well). The wells were incubated for 2 hours at room temperature and washed twice with CovaBuffer as described above. The amount of bound protein was

5 quantified by measuring the peroxidase activity in citrate buffer (0.1 M, pH 5.0) containing 0.015% (v/v) H_2O_2 and 0.6 mg/ml OPD (Sigma cat. no. P 8412) as chromogenic substrate. The enzymatic reaction was terminated after 6 minutes by addition of H_2SO_4 (2M, 100

10 μ l/well), and the color reaction quantified by measuring the absorption at 490 nm on the ELISA reader (InterMed Immuno reader NJ 2000). The results for phenanthrene quinone amine compound no. 3 are shown in Figs. 8a and 8b. On PolySorp[®] surfaces (Fig. 8a) no significant higher

15 signal was observed than the control level, while on Nunclon[®] Delta treated surfaces higher signals were observed for all irradiation times with a maximum with 0.116 mM photoprobe concentration and 5 minutes irradiation time. Results for anthraquinone amine

20 compound no. 5 are shown in Figs. 9a and 9b. On PolySorp[®] surfaces (Fig. 9a) a significant higher signal than the background (control) was clearly seen. Maximum was obtained with a photoprobe concentration between 0.116 mM and 0.0232 mM and 10 minutes irradiation time. On

25 Nunclon[®] Delta treated surfaces significant higher signals than the background (control) were observed at all irradiation times with concentrations of the photoprobe higher than $3.72 \cdot 10^{-5}$ mM.

30 The effect of varying spacer arms was tested on anthraquinone amines compounds nos. 5, 7 and 9. The anthraquinone amines were dissolved in distilled water to a concentration of 0.1 mM photoprobe, and 100 μ l was added to each well of a Nunc-Immuno[®] Module F16 PolySorp

35 and a non-sterile Nunc F96 (Nunclon[®] Delta treated) plate. The plates were placed 10 cm below the UV lamp and

irradiated for 10 minutes. The wells were rinsed three times with demineralized water and dried for 50 minutes at 60 °C. A two-fold dilution series of biotin-succinimide ester in PBS buffer was added (100 µl/well), and the wells were allowed to incubate overnight at room temperature. The wells were washed three times with CovaBuffer, avidin mix was added, and the amount of bound protein quantified as described earlier. The results are shown in Fig. 10 and clearly indicate the effect of the linker length. Compound no. 9, with two β-alanine units, showed the overall highest signal when grafted on PolySorp[®]. Lower signals were seen, when compound no. 9 was grafted on Nunclon[®] Delta treated plates. However, the signal was still higher than for compound no. 5 and compound no. 7, indicating the advantage of having an optimal spacer length between the photoprobe and the primary amino group.

The uniformity of photochemically grafted amino groups on polystyrene surfaces was tested with anthraquinone amine compound no. 9. Compound no. 5 was dissolved in distilled water to a concentration of 0.1 mM photoprobe. 100 µl of the solution was added to each well in four non-sterile Nunc F95 (Nunclon[®] Delta treated) plates, placed 10 cm below the UV lamp and irradiated for 10 minutes. Each well was washed three times with demineralized water and dried for 50 minutes at 60 °C. Biotin-succinimide ester in PBS buffer was added (125 µg/ml, 100 µl/well), and the wells allowed to incubate overnight at room temperature. After washing three times with CovaBuffer avidin mix was added to each well, and the amount of bound protein was quantified as described earlier. The results are shown in Table 2.

TABLE 2

Uniformity of primary amino groups polystyrene surfaces by UV grafting. Mean of four plates.

5

Mean (Abs. 490 nm)	St. dev.	% CV
1.959	0.063	3.2

The storage stability of photochemically grafted amino groups on polystyrene surfaces was tested with anthraquinone amine compound no. 9. Compound no. 5 was dissolved in distilled water to a concentration of 0.1 mM photoprobe. 100 μ l of the solution was added to each well in non-sterile Nunc F96 (Nuncclon[®] Delta treated) plates and Nunc-Immuno[®] Module F8 PolySorp plates (Nunc. cat. no. 469078), placed 10 cm below the UV lamp and irradiated for 10 minutes. Each well was washed three times with demineralized water and dried for 50 minutes at 60 °C. One plate of each type was packed in sealed plastic bags and stored for up to 30 days at 4 °C, 20 °C, 37 °C, and 60 °C. Plates were taken out for testing at intervals of 1, 2, 6, 13, 20, and 30 days of storage. One plate of each type was used for stability testing. The plates were incubated with biotin-succinimide ester followed by avidin mix, and the amount of bound protein was quantified as described earlier. Results are shown in Figs. 11 and 12. All data have been normalized relative to day zero (no storage). The results show that no significant reduction in activity is seen at a store temperature of 37 °C or below, while plates stored at 60 °C showed a slight decrease in signal.

30

Introduction of carboxylic acids onto polystyrene surfaces by UV grafting

The anthraquinone carboxylic acid derivative compound
5 no. 13 was dissolved in 0.1 M LiOH and diluted with
distilled water to a concentration of 5 mM. A two-fold
dilution series of the photoprobe (100 µl/well) was made
in non-sterile Nunc F96 (Nuncclon® Delta treated) plates
and in Nunc-ImmunoR Module F8 PolySorp plates. The plates
10 were placed on a shaker for one hour at 50 °C before UV
irradiation. the wells were aspirated and placed 14 cm
from the UV lamp and irradiated for 10 minutes. Non-
irradiated plates were used as control. The wells were
rinsed three times with demineralized water and crystal
15 violet (Merck cat. no. 1408, 15 mg in 100 ml of distilled
water) added to each well (100 µl/well). The plates were
incubated for 30 minutes at room temperature, washed
three times with demineralized water and dried for 30
minutes at 60 °C. Dissolution of bound crystal violet was
20 done by adding a solution of 1 M HCl in 96% ethanol to
each well. The results were read on an InterMed Immuno
reader NJ 2000 at 590 nm and are shown in Fig. 13. As
crystal violet binds as an ion pair to carboxylic acids,
an increase in signal will indicate the presence of
25 immobilized carboxylic acid groups on the surface. No
signal was obtained on plates that had not been UV
irradiated, while a significant increasing signal with
increasing concentration of the photoprobe was seen on
PolySorp® surfaces.

30

EXAMPLE 4

Covalent coupling of a peptide onto polystyrene surfaces
by UV grafting

35

Peptide compound no. 19, N-terminally anthraquinone substituted, was dissolved in distilled water (0.1 mg/ml).

- 5 100 μ l was added to each well of two Nunc-Immuno[®] Module F16 PolySorp[®] - except for row A - which was used as blank control. One strip (2 x 8 wells) at a time was irradiated 2, 5, 10, 15, 30, and 60 minutes, respectively (14 cm under the UV lamp). After UV irradiation the
- 10 plates were rinsed three times with 0.4 M NaOH containing 0.25% Tween 20^R, and three times with PBS buffer. Immobilized peptide was detected with a monoclonal anti-peptide antibody (culture supernatant Hyb 161-2 from Statens Seruminstitut, Copenhagen, Denmark). A two-fold
- 15 dilution series of the antibody in PBS-Tween[®] buffer was made in the Immuno Modules from row C and onwards (100 μ l/well). In row A (peptide blank) undiluted culture supernatant was added, while row B was used as control without Hyb 161-2. The Immuno Modules were incubated for
- 20 two hours at room temperature, and then washed three times with PBS buffer containing 0.05% Triton X-100^R. A mixture of rabbit anti-mouse (2 μ g/ml DAKO code 2 259) and horse radish peroxidase conjugated goat anti-mouse (1:500, DAKO code P 447) was added to each well (100 μ l),
- 25 incubated for one hour at room temperature and washed three times as described above. OPD substrate (100 μ l) was added to each well, and the substrate reaction was stopped after four minutes with 2 M H₂SO₄ (100 μ l/well). The results are shown in Fig. 14 and clearly show that
- 30 the optimum irradiation time was between 2 and 15 minutes. Optimal dilution factor of Hyb 161-2 culture supernatant was approx. 10 and was used in the subsequent experiments.
- 35 The effect of irradiation time was further investigated. the experiment was done as described above, except that a

5

15

20

25

30

35

leading to soluble photochemical crosslinked peptide aggregates, which is later removed in the washing steps.

The storage stability of the photochemically grafted peptide was investigated. The anthraquinone peptide number 19 was dissolved in distilled water (0.1 mM), and the solution was added to each well of a Nunc-Immuno® Module F16 PolySorp®. The wells were irradiated for 10 minutes (14 cm under the UV lamp) and finally washed as described earlier. the wells were coated with 1% sucrose in PBS buffer (300 µl/well), incubated for one hour at room temperature, then aspirated and dried with compressed air. The plates were packed in sealed plastic bags and stored at 4 °C and 37 °C. The plates were taken out for testing at intervals from 1 to 32 days. ELISA was performed as earlier described, and the data are presented in Fig. 17. All data are normalized relative to day zero. No drop in signal was detected during the storage period, but a storage temperature of 37 °C consistently gave a slightly lower signal than at 4 °C.

EXAMPLE 5

UV grafting of anthraquinone nitrolotriacetic acid (NTA) derivative 20 onto polystyrene surfaces

The anthraquinone NTA derivative 20 was dissolved in phosphate buffer (pH 5.5) to a start concentration of 1 mM. A two fold dilution series of the solution was made in two Nunc-Immuno™ Module F16 PolySorp plates (100 µl/well) and incubated for 1 hour at 50 °C. The wells were aspirated and one plate was placed 14 cm below the UV-lamp (Philips HPA 400) and irradiated with UV-light for 5 minutes while the other plate was kept in the dark as control. All wells were washed with demineralized water followed by the addition of crystal violet solution

(15 mg in 100 ml demineralized water; 100 µl/well) and incubated at r.t. for 30 minutes. The plates were washed with water and dried at 60 °C for 1 hour. Dissolution of bound crystal violet was done by adding a solution of 1M Hcl in ethanol to each well. The results were read on an InterMed Immuno reader NJ 200 at 590 nm. The results are shown in Fig. 11 and shows a significant increase in signal with increasing concentration of the photoprobe. No signal was obtained in the wells that had not been UV-irradiated.

Metal chelates, especially nickel chelates, have been reported to have specific binding properties for histidine tagged peptides and proteins (Hochuli et al., J. Chromat. 411, 177-184 (1987)). To test the ability of the new NTA-derivatized microtitre plates to selectively bind histidine tagged peptides three biotinylated peptides, with and without a hexahistidine tag, were synthesized by standard Fmoc solid phase peptide synthesis (the three peptides were prepared similarly to the anthraquinone substituted peptide (compound 19) in example 1).

Peptide 1:	Biotin-εAhx-Leu-Lys-Leu-Lys-Trp-Lys-OH
Peptide 2:	Biotin-εAhx-Leu-Lys-Leu-Lys-Trp-Lys- <u>His-His-His-His-His-His</u> -OH
Peptide 3:	Biotin-εAhx-Arg-Thr-Gln-Asp-Glu-Asn- Pro-Val-Val-His-Phe-Phe-Lys-Asn-Ile- Val-Thr-Pro-Arg-Thr-Pro-OH

Photocoupling of the anthraquinone substituted NTA derivative was done as described above except that the plate was irradiated with UV-light for 10 min without prior aspiration of the solution. The plate was washed

three times with PBS buffer (pH 7.2) and then charged with nickel by adding NiSO_4 (50 mM in Milli Q water, 100 μl /well). After incubation for 30 min at room temperature the wells were washed three times with Milli Q water.

5 Solutions of each peptide (23 μM , 100 μl /well) in the assay buffer (PBS buffer (pH 7.2) containing 0.05% Tween 20[®] and 500 mM NaCl) were added to separate rows of the plate. Water was added to the rest of the rows as control. The peptides were allowed to incubate overnight

10 at room temperature, then the wells were washed three times with the assay buffer, and avidin mix (100 μl /well, for details see example 3) in the assay buffer added to the wells. After two hours at room temperature the wells were emptied, washed three times with assay buffer, and

15 the amount of immobilized avidin quantified by measuring the peroxidase activity (for details see example 3). The results are shown in Fig. 18a and clearly show that only the histidine tagged peptide gave any significant binding in the nickel chelate plate.

20

EXAMPLE 6

UV-grafting of anthraquinone substituted polyethylene glycol 2000 (AO-CO-PEG2000) derivative 22 onto

25 polystyrene surfaces

The anthraquinone PEG2000 derivative 22 was dissolved in Milli Q water to a concentration of 0.3 mM. Polystyrene slides (from Nunc, Denmark) were rinsed with 96% ethanol

30 (1 x 5 minutes with ultrasonication) and Milli Q water (2 x 5 minutes with ultrasonication) and dried in a non-evacuated desiccator above CaCl_2 (residual water in the atmosphere above the CaCl_2 : 0.14-1.4 mg/l). Before photoimmobilization the slides were brought into

35 equilibrium with the natural water content in the atmosphere. Two slides were placed in a small metal

container and the photoprobe solution added to cover the surface of the slide with approx. 2.5 mm of the solution above the surface. One of the slides was placed 10 cm below the UV-lamp (Philips HPA 400) and irradiated for 5 minutes, while the other slide was kept in the dark as control. Both slides were rinsed thoroughly with Milli Q water from a bottle and then three times with Milli Q water with ultrasonication (3 x 5 minutes). The slides were dried in a non-evacuated desiccator above CaCl₂. As further controls two slides were treated as described above with a solution of PEG2000 (0.3 mM) and another two slides with Milli Q water alone. The effect of the photografting were tested by measuring the advancing contact angles using a VCA-2000 instrument (AST Products, Inc.). Five drops (1.5 - 2.5 µl) of Milli Q water were placed on each slide and the advancing contact angle measured (two contact angles per drop giving 10 contact angles per slide) using the manufacturers software. Prior to each series of measurements, the slides were brought into equilibrium with the natural water content in the atmosphere. The results are shown in Fig. 12 and clearly show a decrease of the advancing contact angle on the anthraquinone substituted PEG2000 photografted polystyrene slide relative to the controls.

25

EXAMPLE 7

UV-grafting of anthraquinone substituted polyethylene glycol 2000 (AO-CO-PEG2000) derivative 22 onto polypropylene surfaces

30

The anthraquinone PEG2000 derivative 22 was dissolved in Milli Q water to a concentration of 0.3 mM. Polypropylene slides (from Nunc, Denmark) rinsed and dried as described for the polystyrene slides (Example 6). Two slides were placed in a small metal container and the photoprobe

35

solution added to cover the surface of the slide with approx. 2.5 mm of the solution above the surface. One of the slides was placed 10 cm below the UV-lamp (Philips HPA 400) and irradiated for 5 minutes, while the other

5 slide was kept in the dark as control. Both slides were rinsed thoroughly with Milli Q water from a bottle and then ten times with Milli Q water with ultrasonication (10 x 5 minutes). The slides were dried in a non-evacuated desiccator above CaCl_2 . As a further control

10 one slide was washed and dried as described above. Advancing contact angle measurements were performed as described for the polystyrene slides. The results are shown in Fig. 13 and clearly show a decrease in the advancing contact angle on the anthraquinone substituted

15 PEG2000 photografted polypropylene slide relative to the controls.

METHOD OF PHOTOCHEMICAL IMMOBILIZATION OF LIGANDS
-----PATENT CLAIMS

5

1. A method of immobilizing a ligand (L) to the surface (P) of a carbon-containing substrate material; said method comprising:

10 a photochemical step of linking of one or more photochemically reactive compounds (Q) to a carbon-containing material surface (P);

said carbon-containing material surface (P) being linked
15 to the photochemically reactive compound (Q) either directly or via one or more spacers (S₁); and

said photochemically reactive compound (Q) being linked
to one or more ligands (L) either directly or optionally
20 via one or more spacers (S) and/or thermochemically reactive compounds (T);

said spacers (S₁) and (S) being, equal or different,
thermochemically or photochemically reactive or non-
25 reactive spacers;

wherein the photochemically reactive compound (Q) is a
quinone compound selected from the group consisting of
monomeric quinone compounds, dimeric quinone compounds,
30 and symmetrical or asymmetrical oligomeric quinone compounds;

said quinone compound (Q) containing a cyclic hydro-
carbon, or from 2 to 10 fused cyclic hydrocarbons, said
35 quinone compound having at least two conjugated carbonyl

groups, the number of which does not exceeding twice the number of fused cyclic hydrocarbons;


5 said quinone compound (Q) optionally being substituted with substituents (R) which do not result in steric hindrance to the immobilization of the ligand (L) or do not disturb the photochemistry; and

10 wherein the photochemical step comprises irradiation of the photochemically reactive compound (Q) with non-ionizing electromagnetic radiation having a wavelength in the range from UV to visible light.

15 2. A method according to claim 1, wherein the irradiation time is generally shorter than 12 hours, preferably less than 200 minutes, more preferably less than 60 minutes, most preferably less than 30.


20 3. A method according to claims 1 or 2, wherein the quinone compound comprises 1-4 fused cyclic hydrocarbons according to the general formulas (XXXVII), (XXXVIII), and (XXXIX) below, wherein the letters m, n and o designate 0 or integers from 1-8, the sum of m, n and o being 8 or less; l indicates 0 or an integer from 1 to
25 two times n; r and q indicate 0, 1 or 2; k indicates 0 or an integer from 1 to 2 times m; and t indicates 0 or an integer from 1 to 2 times o;

5




10

15



20

25



30

35

4. A method according to claim 3, wherein the quinone compound (Q) is selected from the group consisting of anthraquinones (V,VI,VII,X,XI,XIII,XXVIII), phenanthrene-quinones (VIII,IX,XII), benzoquinones (I,II), naphtho-quinones (III,IV,XXVII), and compound (XXVI,XXIX), particularly anthraquinones, phenanthrenequinones, and compound (XXVI).

10

5. A method according to any of claims 1-4, wherein the quinone compound (Q) is substituted with substituents (R) selected from the group consisting of: functional groups comprising $-\text{NO}_2$, $-\text{SO}_3^-$, $-\text{SO}_2^-$, $-\text{CN}$, $-\text{PO}_3^{2-}$, $-\text{PO}_2^-$, $-\text{COOH}$, halogen, i.e. $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, primary amines, secondary amines and tertiary amines, or derivatives thereof; and hydrocarbyls which may be substituted with: $-\text{NO}_2$, $-\text{SO}_3^-$, $-\text{CN}$, $-\text{PO}_3^{2-}$, $-\text{PO}_2^-$, $-\text{COOH}$, halogen, i.e. $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, epoxide, and $-\text{H}$; said hydrocarbyls preferably being alkyls such as methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decanyl, undecanyl, dodecanyl, tridecanyl, tetradecanyl, pentadecanyl, hexadecanyl, heptadecanyl, octadecanyl, nonadecanyl, eicocanyl, straight or branched, with one or more double or triple bonds, and aryls such as phenyl, naphthyl, biphenyl, tolyl, benzyl, cumenyl, mesityl, xylyl, pentalenyl, indenyl.

20

6. A method according to claim 1, wherein the polymer is selected from the group consisting of synthetic and natural polymers such as polystyrene, polyethylene, polyvinylacetate, polyvinylchloride, polyvinylpyrrolidone, polyacrylonitrile, polymethyl-methacrylate, polytetrafluoroethylene, polycarbonate, poly-4-methylpentylene, polyester, polypropylene, cellulose, nitro-

30

cellulose, starch, polysaccharides, natural rubber, butyl rubber, styrene butadiene rubber, silicone rubber.

7. A method according to claim 1, wherein the carbon-
5 containing material (P) is selected from the group
consisting of premodified materials including silica,
glass, controlled pore glass, silica gel, or metal which
materials have been premodified to contain carbon;
monolayer or multilayer films; Langmuir-Blodgett-films;
10 micelles; biological membranes; proteins; nucleotides,
peptide nucleic acids (PNA) and nucleic acid binding
partners, natural or synthetic polymers coated with
biological or organic material.

15 8. A method according to claim 1, wherein the ligands
(L) is a functional group selected from the group
consisting of -COOH (carboxylic acids), sulfonic acid
derivatives, -COOR (esters, including active esters), -
COX (acid halides, acid fluorides and acid chlorides, acid
20 azides or similar active carboxylic acid derivatives), -
CONHNH₂ (acid hydrazides), -NHCONHNH₂ (semicarbazides), -
NHCSNHNH₂ (thiosemicarbazides), -CN (nitriles), -CHO
(aldehydes), RR'CO (ketons), -OH (alcohols), -SH
(thioles), -SSR (disulfides), -NH₂ (amines, including
25 primary, secondary and tertiary amines), -NHNH₂
(hydrazines), -OR (ethers), epoxides, -SR (sulfides), -X
(halides), -NO₂, -CH₃; or derivatives thereof; a non-
functional groups, such as methyl, ethyl, isobutyl,
tertbutyl or aromates; or the ligand is selected from the
30 group consisting of: biologically active molecules, such
as biotin, toxins, herbicides, pesticides, carbohydrates,
antibiotics such as penicillins and other drugs such as
cell poisons, steroids, peptides, nucleotides, peptide
nucleic acids (PNA) and nucleic acid binding partners,
35 proteins and haptens.

9. A method according to claim 1, wherein the spacer (S) is distance making group selected from the group consisting of C₁-C₂₀ alkyl groups such as poly-methylene, optionally containing aromatic or mono/poly-unsaturated hydrocarbons; polyoxyethylene such as poly-ethylene glycol; oligo/polyamides such as poly- β -alanine, poly-glycine, polylysine, peptides; oligosaccharides; oligo/-polyphosphates such as phospho-mono/diesters, mono/-diamides; and oligo/polysulfonic amides/esters; or combined units of the aforementioned or combined units thereof.

10. A method according to claim 1, wherein the thermochemical reactive compound (T) is a compound containing a thermochemical reactive group selected from the group consisting of: -COOH (carboxylic acids), sulfonic acid derivatives, -COOR (esters, comprising active esters), -COX (acid halides, acid azides and similar carboxylic acid derivatives), -CONHNH₂ (acid hydrazides), -NHCONHNH₂ (semicarbazides), -NHCSNHNH₂ (thiosemicarbazides), -CHO (aldehydes), RR'CO (ketones), -OH (alcohols), -X (halides: chloride, bromide, iodide), -SH (thioles), -SSR (disulfides), -NH₂ (amines, comprising primary, secondary and tertiary amines), -NHNH₂ (hydrazines), epoxides, maleimides.

11. A method according to claim 1, comprising the steps of linking a quinone compound (Q) as defined in claim 1 to a ligand (L) to obtain a quinone-ligand conjugate (Q-L), and photoimmobilizing the quinone-ligand conjugate (Q-L) onto the substrate material surface (P) to obtain the substrate material (P-Q-L).

12. A method according to claim 1, comprising the steps of linking a ligand (L) to a spacer molecule (S) by use of a photochemical or a thermochemical compound, linking

the spacer-ligand conjugate (S-L) to a quinone compound (Q) as defined in claim 1 to obtain a quinone-ligand conjugate (Q-S-L) having an intermediate spacer molecule, and photoimmobilizing the quinone-ligand conjugate (Q-S-L) on the substrate surface (P) to obtain the substrate material (P-Q-S-L).

13. A method according to claim 1, comprising the steps of linking at least one quinone compound (Q) as defined in claim 1 to a spacer molecule (S), linking the spacer-quinone conjugate (Q-S) to a ligand (L) to obtain a quinone-ligand conjugate (Q-S-L) having an intermediate spacer molecule, and then photoimmobilizing the quinone-ligand conjugate on the substrate surface (P) to obtain the substrate material (P-Q-S-L).

14. A method according to claim 1, comprising the steps of linking a quinone compound (Q) as defined in claim 1 to a substrate surface (P) to obtain a quinone-substrate surface conjugate (P-Q), photoimmobilizing a ligand (L) to a quinone-substrate surface conjugate (P-Q) to obtain the substrate material (P-Q-L).

15. A method according to claim 1, comprising the steps of linking a spacer molecule (S₁) by use of a photochemical or a thermochemical compound to a substrate surface (P), linking a quinone compound (Q) as defined in claim 1 to the spacer-substrate surface conjugate (P-S₁) to obtain a quinone-substrate surface conjugate (P-S₁-Q) having an intermediate spacer molecule, and photoimmobilizing a ligand (L) to a quinone-polymer surface conjugate.

16. A method according to claim 1, comprising the steps of linking a quinone compound (Q) as defined in claim 1 to a spacer molecule (S), linking the spacer-quinone

conjugate (Q-S) to a substrate surface to obtain a quinone-substrate surface conjugate (P-Q-S) having an intermediate spacer molecule.

5 17. A method according to claim 1, wherein the photo-reaction takes place in an aqueous medium.

18. A method according to 16, wherein the aqueous medium has a pH value in the range of 0-7 or in the range of 7-
10 12.

19. Use of a quinone (Q) as defined in claim 1 for immobilizing a ligand to a carbon-containing substrate material surface (P) according to the method as claimed
15 in claim 1.

20. A carbon-containing material having a ligand (L) immobilized to its surface (P) prepared according to the method as claimed in claim 1.

20

21. Use of a carbon-containing substrate material as prepared according to the method as claimed in claim 1 in a detection system.


25 22. Use of a carbon-containing substrate material as prepared in claim 1 as a carrier for solid phase immunoassays.

23. Use as claimed in claim 22, wherein the carrier is
30 selected from the group consisting of well plates, test particles such as beads and micro spheres, test tubes, test sticks, and test strips.


24. Use of a carbon-containing substrate material as
35 prepared in claim 1 as a carrier for solid phase

synthesis of peptides, oligonucleotides, carbohydrates
and small organic molecules.


Figure 1. (sheet 1/4)




(I)




(II)




(III)




(IV)




(V)




(VI)




(VII)



(VIII)



(IX)



(X)











Figure 1. ^{2/30} (cont. 2/4)


Figure 1. (cont. 3/4)




(xix)




(xx)




(xxi)




(xxii)



(xxiii)



(xiv)



(xxv)

Figure 1. (cont. 4/4)







Figure 2.



6/30




Figure 3.




Figure 4.

8/30




Figure 5.

9/30








Figure 6






10/30






Figure 7. (sheet 1/5)



11/30

Figure 7. (cont. 2/5)



12/30
Figure 7. (cont. 3/5)






13/30
Figure 7. (cont. 4/5)


Figure 7. (cont. 5/5)






Conc. of photoprobe (mM)

Figure 8a



Conc. of photoprobe (mM)

Figure 8b



Conc. of photoprobe (mM)

Figure 9a




Figure 9b




Figure 10




Figure 11




Figure 12




Figure 13




Figure 14




Figure 15




Figure 16




Figure 17




Figure 18a




Figure 18b




Figure 19




Figure 20

INTERNATIONAL SEARCH REPORT

International application No.

PCT/DK 96/00167

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: C08J 7/18, G01N 33/543 // C07K 17/06, C12N 11/06
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: C12N, C07K, G01N, A61K, C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPODOC, MEDLINE, WPI, BIOSIS, DBA

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0319957 A2 (GLUETECH ASP), 14 June 1989 (14.06.89), page 4, line 12 - line 24; page 6, line 14 - line 16 --	1-24
X	US 5292873 A (S.E. ROKITA ET AL), 8 March 1994 (08.03.94) --	1-24
A	WO 9102768 A1 (EPIPHARM ALLERGIE-SERVICE GESELLSCHAFT M.B.H.), 7 March 1991 (07.03.91) -- -----	1-24

☐ Further documents are listed in the continuation of Box C. ☒ See patent family annex.

- | | |
|---|--|
| <ul style="list-style-type: none"> * Special categories of cited documents: * "A" document defining the general state of the art which is not considered to be of particular relevance * "E" earlier document but published on or after the international filing date * "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) * "O" document referring to an oral disclosure, use, exhibition or other means * "P" document published prior to the international filing date but later than the priority date claimed | <ul style="list-style-type: none"> * "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention * "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone * "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art * "&" document member of the same patent family |
|---|--|

Date of the actual completion of the international search

4 July 1996

Date of mailing of the international search report

18 -07- 1996

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Patrik Andersson
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

Information on patent family members

01/04/96

International application No.

PCT/DK 96/00167

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A2- 0319957	14/06/89	CA-A- 1335804	06/06/95
		DE-D, T- 3885908	24/03/94
		EP-A, A, B 0390841	10/10/90
		SE-T3- 0390841	
		JP-T- 3502938	04/07/91
		US-A- 5427779	27/06/95
		WO-A, A- 8905329	15/06/89

US-A- 5292873	08/03/94	NONE	

WO-A1- 9102768	07/03/91	AT-A- 197689	15/10/93
		AT-B- 397723	27/06/94
		AU-A- 6182390	03/04/91
		CA-A- 2039702	22/02/91
		EP-A, A- 0439585	07/08/91
		JP-T- 4502934	28/05/92
		NO-B, C- 176668	30/01/95
		US-A- 5196478	23/03/93

Form PCT/ISA/210 (patent family annex) (July 1992)